

**Table 2 Measurement of casts made from the 3 test materials**

Line	Distance (cm)							
	Fulldent mix		President mix		Xantopren-H mix		Single	Double
	Single	Double	Single	Double	Single	Double		
	Mean (SD)	Mean (SD)	Mean (SD)	Mean (SD)	Mean (SD)	Mean (SD)	Mean (SD)	Mean (SD)
Buccolingual	4.1 (0.8)	4.1 (1.0)	4.0 (1.6)	4.0 (0.2)	4.5 (0.6)	4.1 (1.6)		
Mesiodistal	2.8 (0.7)	2.9 (1.1)	2.9 (1.5)	2.9 (1.2)	3.0 (0.8)	3.0 (0.2)		
Diagonal	5.0 (0.3)	5.1 (1.2)	5.1 (1.7)	5.1 (0.8)	5.1 (0.9)	5.1 (1.0)		

*SD = standard deviation.*